

# MACHINE CAST LEAD



<b>MANUFACTURING PROCESS</b>	Single drum continuous casting	<b>TOLERANCES</b>	+/-5%
<b>PURITY</b>	<b>99.9+ %</b> Pure lead	<b>NOMINAL THICKNESS</b>	Codes 1-8
<b>QUALITY STANDARDS</b>	BBA 86/1764, British Board of Agreement Standard for Machine Cast lead	<b>MANUFACTURER'S GUARANTEE</b>	

## SPECTRO ANALYSIS OF CAST LEAD (Data from a previous batch)

Element	Cu	Zn	Ag	Sn	Bi	Sb	Cd	As	Ni	Na	Ca	Al	Pb
Concentration (%)	0.03 - 0.06	0.00026	0.0022	0.001	0.0235	0.0014	0.00012	0.0004	0.00046	0.00028	0.0015	<0.00010	99.97

